



## Plastics Specific Test Instructions

---

Please review the following information before testing.

Participants in the Tensile Properties, Flexural Properties, Coefficient of Friction and Optical Properties tests will notice that the results for each property is reported on a separate data sheet. It is not required that participants report results for all properties in multiple property tests.

Please return **all** data sheets to CTS for processing. If you are not reporting data for a test or property, RETURN THE BLANK DATA SHEET TO CTS.

If you are faxing the data sheets to CTS, you **MUST** use a cover sheet indicating the total number of pages you are sending. CTS will contact participants if the number of data sheets received is less than what is indicated on the cover page.

<u>Analysis</u>	<u>Analysis Name</u>
<u>704-708</u>	<u>Tensile Properties (ASTM)</u>
<u>710</u>	<u>Deflection Temperature Under Flexural Load 1.82 MPa (ASTM)</u>
<u>711</u>	<u>Deflection Temperature Under Flexural Load .455 MPa (ASTM)</u>
<u>712</u>	<u>Temperature of Deflection Under Load 1.80 MPa (ISO)</u>
<u>715-716</u>	<u>Vicat Softening Temperature</u>
<u>718</u>	<u>Specific Gravity</u>
<u>720-722</u>	<u>Flexural Properties (ASTM)</u>
<u>730-734</u>	<u>Tensile Properties (ASTM)</u>
<u>736-738</u>	<u>Flexural Properties (ISO)</u>
<u>750</u>	<u>Flow Rates of Thermoplastics</u>
<u>755</u>	<u>Moisture Content of Plastics</u>
<u>757</u>	<u>Ash Content in Thermoplastics</u>
<u>770-776</u>	<u>Tensile Properties of Films</u>
<u>780-781</u>	<u>Coefficient of Friction</u>
<u>782</u>	<u>Tear Resistance of Films</u>
<u>785-786</u>	<u>Optical Properties of Films</u>
<u>790</u>	<u>Notched Izod Impact</u>
<u>792</u>	<u>Notched Charpy Impact</u>

# Plastics Specific Test Instructions

## Tensile Properties, ASTM Method

**Analysis:** 704 - 708

**Pack:** PT

**Sample Code:** F

**Test Method:** ASTM D638

**Properties Measured:** Tensile Stress at Yield, Tensile Stress at Break, Percent Elongation at Yield, and Modulus of Elasticity (tangent). Participants may choose which of these four properties to measure and report. **Yield Point is defined as per ASTM D638-03, A2.22 (Zero Slope).**

**Test Parameters:** See *Material* section of data sheets for speed of testing.

**Sample Information:** Seven specimens have been provided for each sample. Report test results for five specimens. Two specimens from each sample may be used for equipment set up or substitution if one of the five specimens appears flawed. Samples selected according to manufacturer specifications not to exceed 100% elongation. The elongation ranges are approximate.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report test results with the precision listed below. Although participants may report stress and modulus data using other units (such as psi, ksi, MPa, kgf/mm<sup>2</sup>), please report data with comparable precision.

Tensile Stress at Yield - To nearest whole number for psi

Tensile Stress at Break - To nearest whole number for psi

Percent Elongation at Yield - To nearest 0.01%

Modulus of Elasticity - To nearest 0.1 for ksi

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (*psi is the default unit for Tensile Stress at Yield and Tensile Stress at Break values, percent is the default unit for Elongation at Yield values, ksi is the default unit for Modulus of Elasticity values*).

# Plastics Specific Test Instructions

## Deflection Temperature - 1.82 MPa (264 psi) - ASTM Method

**Analysis:** 710

**Pack:** DT

**Sample Code:** E

**Test Method:** ASTM D648

**Properties Measured:** Deflection temperature under flexural load.

**Test Parameters:** 1.82 MPa (264 psi) maximum fiber stress. Specimen in edgewise position.

**Sample Information:** Five specimens have been provided for each sample. Sufficient number of specimens have been provided for four measurements per sample. One extra specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** Many laboratories have the capability to test several specimens simultaneously. If you test more than one bar at a time, use an equal number of specimens from each sample. Do not test all four specimens of one sample at one time.

**How to Report Data:** Report data in ***degrees Celsius*** to the first decimal place.

**Additional Information to Report:** Please indicate in space marked CONDITIONS at the bottom of the data sheet which method (A or B) was used. Method A requires a 101.6 mm (4 inch) span and Method B requires a 100 mm (3.937 inch) span. If you are uncertain which method/span your instrument complies with, contact the instrument manufacturer. If your instrument has adjustable supports, use the span length you normally use for ASTM D648 measurements.

# Plastics Specific Test Instructions

## Deflection Temperature - 0.455 MPa (66 psi) - ASTM Method

**Analysis:** 711

**Pack:** HD

**Sample Code:** G

**Test Method:** ASTM D648

**Properties Measured:** Deflection temperature under flexural load.

**Test Parameters:** 0.455 MPa (66 psi) maximum fiber stress.

**Sample Information:** Five specimens have been provided for each sample. Sufficient number of specimens have been provided for four measurements per sample. One extra specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** Many laboratories have the capability to test several specimens simultaneously. If you test more than one bar at a time, use an equal number of specimens from each sample. Do not test all four specimens of one sample at one time.

**How to Report Data:** Report data in *degrees Celsius* to the first decimal place.

**Additional Information to Report:** Please indicate in space marked CONDITIONS at the bottom of the data sheet which method (A or B) was used. Method A requires a 101.6 mm (4 inch) span and Method B requires a 100 mm (3.937 inch) span. If you are uncertain which method/span your instrument complies with, contact the instrument manufacturer. If your instrument has adjustable supports, use the span length you normally use for ASTM D648 measurements.

# Plastics Specific Test Instructions

## Temperature of Deflection Under Load - 1.80 MPa - ISO Method

**Analysis:** 712

**Pack:** HI

**Sample Code:** N

**Test Method:** ISO 75, Method A

**Properties Measured:** Temperature of deflection under load, in degrees Celsius

**Test Parameters:** 1.80 MPa maximum nominal surface stress. Specimen in flat position.

**Sample Information:** Five specimens have been provided for each sample. Sufficient number of specimens have been provided for four measurements per sample. One extra specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** Many laboratories have the capability to test several specimens simultaneously. If you test more than one bar at a time, use an equal number of specimens from each sample. Do not test all four specimens of one sample at one time.

**How to Report Data:** Report data in *degrees Celsius* to the first decimal place.

# Plastics Specific Test Instructions

## Vicat Softening Temperature

**Analysis:** 715 - 716

**Pack:** VH & VR

**Sample Code:** H, R

**Test Method:** ASTM D1525

**Properties Measured:** Vicat softening temperature Rate A and Rate B. Participants may report for one or both heating rates. A load of 10N is used with both heating rates.

**Test Parameters:** Use a 10 N load with Heating Rate A ( $50 \pm 5^\circ\text{C/h}$ ) for Pack VH.  
Use a 10 N load with Heating Rate B ( $120 \pm 5^\circ\text{C/h}$ ) for Pack VR.

**Sample Information:** Four specimens have been provided for each sample. One extra specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Cut two test pieces from the center portion of each bar. Prepare a total of six test pieces per sample. Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** Many laboratories have the capability to test several specimens simultaneously. If you test more than one bar at a time, use an equal number of specimens from each sample. Do not test all four specimens of one sample at one time.

**How to Report Data:** Report data in *degrees Celsius* to the first decimal place.

# Plastics Specific Test Instructions

## Specific Gravity

**Analysis:** 718

**Test Method:** ASTM D792, ASTM D1505, or ISO 1183

**Pack:** SG

**Properties Measured:** Specific gravity 23/23°C

**Sample Information:** Report three determinations for each sample. Sufficient sample has been provided for at least three specimens.

**Sample Preparation:** If bars need to be cut into smaller pieces before testing, use the center portion of the bar. Do not use the ends of the bars. Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** Do not report density.

**How to Report Data:** Report data in *sp gr 23/23 °C* to the fourth decimal place.

# Plastics Specific Test Instructions

## Flexural Properties - ASTM Method

**Analysis:** 720 - 722

**Test Method:** ASTM D790, Procedure A

**Pack:** FM

**Properties Measured:** Flexural Modulus (tangent), Flexural Stress at Yield and Flexural Stress at 5% Strain. Participants may choose which of these three properties to measure and report.

**Test Parameters:** Support span of 2 inches (50.8 mm)  
Rate of crosshead motion of 0.05 in/min (1.27 mm/min)  
(Please note that this is the actual crosshead speed, not a strain rate.)

**Sample Information:** Six specimens have been provided for each sample. Report test results for five specimens per sample. One specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report test results with the precision listed below. For units other than those listed below, report data with comparable precision.

Flexural Modulus - To nearest 0.1 for ksi

Flexural Stress at 5% Strain - To nearest whole number for psi

Flexural Stress at Yield - To nearest whole number for psi

**Verify that pre-printed units on the data sheet are correct.** If not, select and indicate one of the valid units listed on the datasheet (*ksi is the default unit for Flexural Modulus, psi is the default unit for Flexural Stress at 5% Strain and Flexural Stress at Yield*).

# Plastics Specific Test Instructions

## Tensile Properties - ISO Method

**Analysis:** 730 – 734

**Test Method:** ISO 527

**Pack:** TI

**Properties Measured:** Tensile Stress at Yield, Tensile Stress at Break, Percent Strain at Yield, and Modulus of Elasticity (chord). Participants may choose which of these four properties to measure and report. Please note that name of Percent Elongation at Yield has been changed to Percent Strain at Yield to be consistent with the terminology in ISO 527.

**Test Parameters:** See *Material* section of data sheets for speed of testing

**Sample Information:** Fourteen specimens have been provided for each sample. Sufficient number of specimens have been provided to measure modulus of elasticity using separate specimens at 1 mm/min. Report test results for five specimens for each property. Four specimens from each sample may be used for equipment set up or substitution if one of the specimens appears flawed. Samples selected according to manufacturer specifications not to exceed 100% elongation. The elongation ranges are approximate.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report test results with the precision listed below. For units other than those listed below report data with comparable precision. Use metric units only.

Tensile Stress at Yield - To nearest 0.01 for MPa

Tensile Stress at Break - To nearest 0.01 for MPa

Percent Strain at Yield - To nearest 0.01%

Modulus of Elasticity - To nearest whole number for MPa

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (*MPa is the default unit for Tensile Stress at Yield and Tensile Stress at Break values, percent is the default unit for Percent Strain at Yield values, MPa is the default unit for Modulus of Elasticity values*).

# Plastics Specific Test Instructions

## Flexural Properties - ISO Method

**Analysis:** 736 - 738

**Test Method:** ISO 178

**Pack:** BP

**Properties Measured:** Flexural Modulus (chord), Flexural Stress at Yield and Flexural Stress at 3.5% Strain. Participants may choose which of these three properties to measure and report.

**Test Parameters:** Speed of testing 2 mm/min. Support span of 64 mm.

**Sample Information:** Six specimens have been provided for each sample. Report test results for five specimens per sample. One specimen from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** Condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report test results with the precision listed below.

Flexural Modulus - To nearest whole number for MPa

Flexural Stress at 3.5% Strain - To nearest 0.01 for MPa

Flexural Stress at Yield - To nearest 0.01 for MPa

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (***MPa** is the default unit for Flexural Modulus, Flexural Stress at 3.5% Strain and Flexural Stress at Yield values*).

# Plastics Specific Test Instructions

## Flow Rates of Thermoplastics

**Analysis:** 750

**Test Method:** ASTM D1238 or ISO 1133, Procedure A or B

**Pack:** R1 (190°C testing temperature) or R2 (230°C testing temperature)

**Properties Measured:** Melt mass flow rate (MFR)

**Test Parameters:** *See data sheet for temperature and load. If using ISO 1133 Procedure B, adjust the travel arm distance to 6.35 mm ( ± 0.25 mm).*

**Sample Information:** Sufficient material has been provided to complete at least two measurements per sample. Participants may use the extra material for retests or determining melt densities for Procedure B.

**Sample Preparation:** Drying of the samples is not needed.

**Special Requirements:** All participants must report results in grams per 10 minutes. Do not report melt volume flow rate (MVR). Laboratories using Procedure B must determine the melt densities for the samples by measuring the mass of a known volume of extruded resin. Melt densities are not provided by CTS.

**How to Report Data:** Report data in ***g/10 min*** to the first decimal place.

# Plastics Specific Test Instructions

## Moisture Content of Plastics

**Analysis:** 755

**Test Method:** ASTM D6869/ISO 15512, Method B; ASTM D6980

**Pack:** MC

**Properties Measured:** % Moisture

**Determine the "as received" moisture of the samples; do not condition the samples prior to testing.**

### Test Parameters:

The resin for this analysis is listed on the data sheet. For ASTM D6869 and ISO 15512, Method B (Karl Fischer reaction) assume that the expected moisture content (w) is *> 1.0% for Polyamides, and between 0.1% and 0.5% for all other resins.*

Participants using ASTM D6869 should refer to section 10.9 of the test method to determine the optimum heating temperature. Participants using ASTM D6980 (weight loss technique) should refer to the annex of the test method for the suggested test conditions for this resin.

**Sample Information:** Participants receive two 35 gram samples of pellets.

Three spaces are provided on the data sheet to report maximum of 3 readings per sample. However, if your lab's procedure is to provide only fewer readings, you may report according to your laboratory's normal procedures.

**Sample Preparation:** To prevent moisture pick-up before testing, test the samples immediately after removing them from the sealed packet.

**How to Report Data:** Report data in % Moisture to the third decimal place (nearest 0.001%)

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet ( **% (percent)** is the default unit for Moisture Content).

# Plastics Specific Test Instructions

## Ash Content in Thermoplastics

**Analysis:** 757

**Test Method:** ASTM D5630

**Pack:** AS

**Properties Measured:** Ash Content as % of mass

**Test Parameters:** *See data sheet for the sample resin; assume all resins will exceed 10% Ash Content. Use the resin type to determine the sample size (grams), furnace temperature ( °C) and ashing duration (mins.) from the test method for the procedure employed.*

**Sample Information:** Please report two determinations for each sample. Sufficient material has been provided to complete at least two measurements per sample; additional material may be used for procedure setup or additional testing.

**Sample Preparation:** Drying of the samples is not needed.

**How to Report Data:** Report data in *Percent of mass* to the second decimal place (nearest 0.01%).

# Plastics Specific Test Instructions

## Tensile Properties of Films

*If you are testing for Secant Modulus (Tests 775-776), please refer to the following page for sample preparation instructions before cutting samples for testing.*

**Analysis:** 770 – 774

**Test Method:** ASTM D882

**Pack:** FB

**Properties Measured:** Tensile Stress at Yield, Tensile Stress at Break, Percent Elongation at Yield, and Percent Elongation at Break. Participants may choose which of these four tensile properties to measure and report. Additionally, participants are asked to report Thickness of Film Tensile Specimens.

**Test Parameters:** Initial Grip Separation of 2 inches (50 mm).  
Rate of grip Separation 20 in/min (500 mm/min).  
Specimen Width 1 inch (25 mm).

**Sample Information:** Each sample pack should contain 7 folded sheets per sample. The top and bottom specimens are provided as cover and may be discarded or used for instrument setup. The cover sheet in each sample is labeled with the sample code for this round. Please mark them with this code. Sufficient material is supplied for 10 determinations per sample. This test uses the same sample pack as Secant Modulus (Tests 775-776); labs reporting for both properties should leave sufficient material to provide the additional samples needed for that test.

**Sample Preparation:** Separate and condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test. Cut all test pieces with the long direction parallel to the **folded edge** of the specimen.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report test results to the following precision. For units other than those listed (such as MPa) report data with a comparable precision.

Tensile Stress at Yield - To nearest whole number for psi  
Tensile Stress at Break - To nearest whole number for psi  
Percent Elongation at Yield - To nearest 0.1%  
Percent Elongation at Break - To nearest whole number  
Thickness of Film - To nearest 0.01 for mils

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (*psi is the default unit for Tensile Stress at Yield and Tensile Stress at Break values, percent is the default unit for Percent Elongation at Yield and Percent Elongation at Break values and mil is the default unit for Thickness of Film*).

# Plastics Specific Test Instructions

## Tensile Properties of Films (Secant Modulus)

**Analysis:** 775 – 776

**Test Method:** ASTM D882

**Pack:** FB

**Properties Measured:** Secant Modulus at 1% Strain, Secant Modulus at 2% Strain. Participants may choose which of these properties to measure and report.

**Recommended Test Parameters:** Initial Grip Separation of 10 inches (250 mm).  
Rate of grip Separation 1 in/min (25 mm/min).  
Specimen Width 1 inch (25 mm).

*The above parameters are recommended by Collaborative Testing Services. If your lab cannot test for these parameters, please contact CTS for further instruction.*

**Sample Information:** Each sample pack should contain 7 folded sheets per sample. The top and bottom specimens are provided as cover and may be discarded or used for instrument setup. The cover sheet in each sample is labeled with the sample code for this round. Please mark them with this code. Sufficient material is supplied for 10 determinations per sample. This test uses the same sample pack as Tensile Properties (Tests 770-774); labs reporting for both properties should leave sufficient material to provide the additional samples needed for that test.

**Sample Preparation:** Separate and condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test. Cut all test pieces with the long direction parallel to the **folded edge** of the specimen.

**How to Report Data:** For the purposes of this interlaboratory testing program, please report Secant Modulus to the nearest whole number for psi. For units other than those listed (such as MPa) report data with a comparable precision.

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (*psi is the default unit for, Secant Modulus at 1% and 2% strain values,*).

# Plastics Specific Test Instructions

## Coefficient of Friction

**Analysis:** 780 - 781

**Test Method:** ASTM D1894

**Pack:** FP

**Properties Measured:** Static coefficient of friction and kinetic coefficient of friction. Film to film COF is measured. Participants may report for either or both types of COF.

**Test Parameters:** 200 gram sled. Sled/Plane speed 150 mm/min.

**Sample Information:** Each sample pack should contain 7 folded sheets per sample. The top and bottom specimens are provided as cover and may be discarded or used for instrument setup. The cover sheet in each sample is labeled with the sample code for this round. Please mark them with this code. Sufficient material is supplied for at least 5 determinations per sample.

**Sample Preparation:** Unfold, separate, and condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test. For each determination, cut the sled test piece from one side of an unfolded specimen and the base test piece from the other side of the same specimen. The inside surfaces of the specimens are to be tested so be careful to maintain test piece orientation. Cut all test pieces with the test direction parallel to the **folded edge** of the sample.

**Special Requirements:** Wait 30 seconds after placing the sled on the plane before starting the test.

**How to Report Data:** Report *COF* data to the nearest 0.001

# Plastics Specific Test Instructions

## Tear Resistance of Films

**Analysis:** 782

**Test Method:** ASTM D1922

**Pack:** FQ

**Properties Measured:** Tearing force per ply.

**Test Parameters:** Use constant radius specimen only.

**Sample Information:** Each sample pack should contain 7 folded specimens per sample. The top and bottom specimens are provided as cover and may be discarded or used for instrument setup. The cover sheet in each sample is labeled with the sample code for this round. Please mark them with this code. Report 10 determinations for each sample. Sufficient material is supplied for up to 30 test pieces per sample.

**Sample Preparation:** Unfold, separate, and condition specimens for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

Cut the constant radius specimens with the slit parallel to the **folded edge** of the sample, to produce specimen tearing in the machine direction. Transverse direction tear resistance is not measured.

**Special Requirements:** Test using one ply. Choose a pendulum so that the scale reading is between 20 and 60 percent of full scale. If your instrument does not satisfy these requirements, contact CTS before testing the samples.

**How to Report Data:** Report data to the nearest whole number for gf/ply. For other units, use comparable precision.

**Verify that pre-printed units on the data sheet are correct.** If not, select and indicate one of the valid units listed on the datasheet (**gf (per ply)** is the default unit for Tearing Force per Ply).

# Plastics Specific Test Instructions

## Optical Properties of Films

**Analysis:** 785 - 786

**Test Method:** ASTM D1003

**Pack:** FD

**Properties Measured:** Percent haze and total luminous transmittance. Participants may report for either or both properties.

**Test Parameters:** Place specimen at the entrance port of the integrating sphere.

**Sample Information:** Each sample pack should contain 6 folded sheets per sample. The top and bottom specimens are provided as cover and may be discarded or used for instrument setup. The cover sheet in each sample is labeled with the sample code for this round. Please mark them with this code. Material is supplied for at least 8 determinations per sample.

**Supplied specimens are folded. Please ensure that the butterfly is opened prior to testing.** A blade may be used in opening butterfly; avoid any damaged sections when measuring.

**Sample Preparation:** Unfold, separate, and condition specimens for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test. Cut one test piece from each side of the unfolded specimen.

**Special Requirements:** Indicate on the data sheet in the “Conditions” section which procedure (A or B) of ASTM D1003 was used and whether CIE Illuminant C or A was used.

**How to Report Data:** Report data to the nearest 0.1% for Transmittance and 0.01 % for Haze.

# Plastics Specific Test Instructions

## Notched Izod Impact - ASTM Method

**Analysis:** 790

**Test Method:** ASTM D256, Method A

**Pack:** IZ

**Properties Measured:** Izod impact resistance of notched specimens.

**Sample Information:** Seven specimens have been provided for each sample. Report test results for five specimens. The additional specimens from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** DO NOT CUT BARS IN HALF. Cut one specimen from the center of each bar. You will create 5 or 6 specimens per sample. Notch all specimens and condition for at least 40 hours at a temperature of  $23 \pm 2^{\circ}\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** In the space provided on the data sheet, indicate all break types observed for the two samples by circling the appropriate codes (C, H, P, NB). It is not necessary to indicate the break type for each specimen.

**How to Report Data:** Report data to the nearest 0.01 for ft.lbf./in or whole number for J/M.

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet (*ft.lbf/in is the default unit for Izod Impact Resistance*).

# Plastics Specific Test Instructions

## Notched Charpy Impact - ISO Method

**Analysis:** 792

**Test Method:** ISO 179

**Pack:** CH

**Properties Measured:** Charpy impact strength of notched specimens.

**Test Parameters:** Test specimens edgewise using notch type A.

**Sample Information:** Seven specimens have been provided for each sample. Report test results for five specimens. Two specimens from each sample may be used for equipment set up or substitution if one of the specimens appears flawed.

**Sample Preparation:** DO NOT CUT BARS IN HALF. Cut one specimen from the center of each bar. You will create 5 - 7 specimens per sample. Notch all specimens and condition for at least 40 hours at a temperature of  $23 \pm 2^\circ\text{C}$  and  $50 \pm 10\%$  relative humidity prior to performing the test.

**Special Requirements:** In the space provided on the data sheet, indicate all break types observed for the two samples by circling the appropriate codes (C, H, P, NB). It is not necessary to indicate the break type for each specimen.

**How to Report Data:** Report data to the nearest  $0.01 \text{ kJ/m}^2$

**Verify that pre-printed units on the data sheets are correct.** If not, select and indicate one of the valid units listed on the datasheet ( *$\text{kJ/m}^2$  is the default unit for Charpy Impact Strength*).